



Elevation









Item:	Description:	Specified:
1	Glass	GFP16
2	Gasket	cc 12x5mm
3	Fixing	50mm steel screws at 250mm centres (30° to glass)
4	Packer	Non-combustible setting blocks at base
5	Bead	27x27mm timber bead, counterbored, screwed, with brass washers
6	Liner 1	32x79mm timber liner, minimum density 640 kg/m³
7	Door Mullion	44x79mm timber liner, minimum density 640 kg/m³
8	Intumescent	2x beads of FD30 mastic

C-C (1:4)

Title Fire Screen Elevation SD

Code FD30/30 - GFP16

Sheet 1 of 2 Date 20/05/2012

Issue 1 Dwg No FZD0258






) 01403 711 126

≥ sales@forza-doors.com



Notes:

- 1 All joints to be sealed using non-thermally softening adhesive.
- 2 Do not allow any contact of the glazing's edge with water.
- 3 Do not install in locations where the glass temperature in normal circumstances might exceed 45 $^{\circ}$ C.
- 4 Avoid all glass to metal contact.
- 5 Do not exercise any restraint on the glazing.
- 6 Do not damage the glazing's edges nor the protection tape.
- $\ensuremath{\mathsf{7}}$ Keep the rebates dry and free from agressive products (acids, organic solvents, etc.).
- 8 Use non-combustible setting blocks at base.
- $\boldsymbol{9}$ Provide clearances of 4-5mm from glass edge to all peripheral framework.
- 10 Provide clearances of 4-5mm from glass face to the beads, using designated gasket.
- 11 Apply a neutral silicone sealant immediately after glazing.
- 12 Frames fix to supporting construction at 600mm centres on jambs and head, min 200mm from ends. 75mm screws min.
- 13 Gap between frame and supporting construction should be sealed with suitable (FD30) mastic.




itle Fire Screen Elevation SD

e FD30/30 - GFP16

Sheet 2 of 2 Date 20/05/2012

Issue 1 Dwg No FZD0258





J 01403 711 126

≥ sales@forza-doors.com